

Fiber Post-Has it Evolved yet-An Evidence Based Analysis?

Noor Saira Wajid Najma Hajira*

Department of Conservative Dentistry and Endodontics Vokkaligara Sangha Dental College and Hospital, KR Road, Next To-KIMS Hospital Visvesvarapuram, Bengaluru, Karnataka, India

*Corresponding author: Noor Saira Wajid Najma Hajira, Department of Conservative Dentistry and Endodontics Vokkaligara Sangha Dental College and Hospital, KR Road, Next To-KIMS Hospital Visvesvarapuram, Bengaluru, Karnataka, India, Tel: 080 2661 8066, E-mail: dr.noorsaira@gmail.com

Citation: Noor Saira Wajid Najma Hajira (2018) Fiber Post-Has it Evolved yet-An Evidence Based Analysis. J Dent Oral Care Med 4(2): 201

Abstract

The restorative rehabilitation of extensively damaged endodontically treated teeth often requires an endodontic post as an additional retention element for core build up. Fiber reinforced post is gaining popularity due to their numerous advantages over metal posts. However, there is no published literature on the disadvantages of the fiber-based post systems. This is the first article which reviews the disadvantages and survival rate of fiber post and also compares the performance of fiber post to metal post systems.

Keywords: Advantages; Disadvantages; Failure; Fiber post

Introduction

The ultimate aim of a post-endodontic restoration is not only to rehabilitate the tooth to function but also prevent the occurrence secondary endodontic infection by providing a good seal as contamination of the root canal system during or after restorative treatment is considered an important factor in the ultimate success or failure. When the tooth has lost a large proportion of its structure, auxiliary means are required to ensure retention of the filling material [1]. Intraradicular posts are used for this purpose in teeth that have undergone root canal treatment [2]. Fiber based post were introduced to overcome the disadvantages of cast metal post i.e loss of retention, root fractures, corrosion, discoloration, necessity of removal of extensive root structure, stress concentration and cannot be used when aesthetic requirement is high [3]. The excellent mechanical properties of Fiber Reinforced Composite materials (FRC) have been used in a diverse range of industrial applications for decades in various sports equipment, and aircraft industry. FRC's was introduced as an alternative to conventional materials for use as endodontic posts. It was suggested that the metallic materials used as posts had a higher modulus of elasticity than the supporting dentin, and this mismatch in modulus could lead to stress concentration in the cement lute leading to failure. This lead to the search for a plastic based material that has a modulus closer to that of dentin.

Fiber post is said to be advantageous due to its lower elasticity modulus leading them to behave similarly to dentine and show similar stress patterns under external impacts which prevents catastrophic fractures, to be able to bond tooth structure which prevents microleakage and also there aesthetic nature which allows there use in aesthetic regions [4-6]. However much emphasis is not been made on the drawbacks of fiber post restorations. Although prefabricated fiber posts have been assessed through various in vitro settings, an analysis of data collected by clinical trials is a more reliable form of evidence-based information on these systems which are suggested to be more beneficial over metallic-intraradicular structures. So the aim of this article was to review the various drawbacks of fiber post restorations and to assess if the fiber-based post has evolved enough to replace custom cast post.

Need for Fiber Post

FRC posts contain a high volume percentage of continuous reinforcing fibers of either carbon, silica or polyethylene embedded in either epoxy based or methacrylate-based polymer matrix which keeps the fibers together [7]. The two main advantages of fiber post are aesthetics and ability to form a monoblock. The term monoblock, literally meaning a single unit. Two prerequisites are simultaneously required for a monoblock to function successfully as a mechanically homogenous unit. First, the materials that constitute a monoblock should have the ability to bond strongly and mutually to one another, as well as to the substrate with which the monoblock is intended to reinforce. Second, these materials should have moduli of elasticity that are similar to the substrate [8,9].

Modulus of Elasticity of Fiber Post – A Flipping Coin

In vitro studies based on three-point bending tests of fiber-based suggest that the success of fiber post is said to be due to their good retention properties under mechanical strain as a result of their low elastic modulus, compared with metal posts which are ten times greater than that of dentin [10,11]. But what is contradictory is that the elastic modulus of dentin ranges from 16-18Gpa. However, the modulus of elasticity of fiber-based post varies among manufacturers in a range between 18-42 Gpa [2,12]. And also the rigidity is not only dependent on the modulus of elasticity but also on the diameter of the post. It is stated that for a post with a modulus of elasticity similar to dentin, to have flexibility similar to dentin, should have a diameter equal to that of dentin. However as the required post diameter is always lesser than that of the radicular dentine diameter, the post becomes more flexible [13]. The unanswered question is whether having a “flexible” post allows movement of the core, resulting in increased microleakage under the crown. This question is especially important when there is minimal remaining coronal tooth structure. Because the post is considerably thinner than the tooth, it may be necessary that the post has a higher modulus of elasticity (greater stiffness) to compensate for the smaller diameter. Posts and core foundations are subjected to repeated lateral forces in clinical function. Because nonrigid posts have a modulus of elasticity and flexural strength close to that of dentin, they flex under occlusal load [14]. The beneficial claims of the fiber post root dentin monoblock could not be validated in independent in vitro and retrospective in vivo studies [15-17].

This flexural will lead to two types of failures i.e cohesive and adhesive failure. Fiber posts were shown to lose flexural strength if they are submitted to cyclic loading or to thermocycling due to degradation of the matrix in which the fibers are embedded [2,18,19]. This degradation leads to water sorption and solubility of fiber composites, which vary according to the brand and the homogeneity of the polymer. This affects the hydrolytic stability of the fiber posts and is found to reduce the strength and stiffness considerably, due to epoxy degradation [20]. Torbjorner *et al.* 1996 examined carbon-fiber posts using SEM and concluded that failures occurred in the fiber-matrix interface and as microcracks within the matrix [21]. Hence this utilization in the oral environment enhances their degradation and potentially shortens their clinical life. This can be termed as a form of cohesive failure.

Many in vivo studies stated that insufficient post rigidity leads to excessive deformation and stress concentration zone during function giving rise to marginal failure [22,23]. Also when the type of tooth contact was taken into consideration, it was determined that teeth with no proximal contacts were more prone to failure compared to those having at least one contact. Also, teeth restored with single crowns were associated with higher failure rates compared to fixed bridges. The authors commented that such a result in terms of the presence of contacts was expected as neighboring teeth helped the distribution of occlusal forces. As for single crowns being more prone to failure, an explanation was made as the forces acting on these teeth being in the vestibular-oral direction in spite of the presence of contacts [5]. This kind of marginal failure between the luting cement and dentin will lead to microleakage and is termed as the preliminary failure. Continuous microleakage will cause a break in the bond between the luting cement and dentin along the length of the root and ultimately results in debonding. Cagidiaco 2007 evaluated the 2-year outcome of restorative procedures involving the placement of fiber posts in endodontically treated teeth concluded that the major failure types associated with this treatment type were post debonding reported as 4.3% and endodontic failures reported as 3.0%. Therefore stating that microleakage in fiber-based posts leads to either persistence or emergence of a secondary endodontic infection. Hence such kind of failure is an adhesive failure [24].

Bonding – The Controversial Factor

The basic problems with resin-based restorative materials shrink from 2% to 7%. This shrinkage generates forces of contraction [25,26]. The force of polymerization contraction result in gap formation along the surface with the weakest bond [27]. This weak link in fiber-based post systems is not only between radicular dentin and luting cement but also between luting cement and fiber post. The bond strength required to overcome such forces of polymerization shrinkage is at least 15-24Mpa. Deterioration of the resin bond over time, which is also significantly increased with functional forces leads to interfacial leakage [28-38]. The addition problems in the radicular dentin are the C factor, any ratio greater than 3:1 is considered unfavorable for bonding. Because of this unfavorable geometry, it is not possible to achieve the gap-free interface with current materials and gap formation increases with time and also the bond strength achieved is only 2-5mpa [39-41]. In the root canal system, the ratio might be 100:1, because virtually every dentin wall has an opposing wall and there are minimal unbonded surfaces. Further recent work shows that C factor more than 1000 in root canals [8]. Because of this unfavorable geometry, it is not possible to achieve the gap-free monoblock suggested in the advertisements of some products and this gap formation increases with time [41]. Adhesion to radicular dentin is reported to be more unpredictable than to coronal dentin, so the quality of the bond may be somewhat compromised and subject to degradation. Because of morphological differences in radicular dentin (i.e. reduction in dentinal tubule density and altered collagen expression and consequently, less resin tag formation during bonding procedures [42,43]. Adhesion is more problematic in apical dentin compared with coronal dentin [42,44,45].

In some apical areas, the dentin is irregular and devoid of tubules [44]. After bonding procedures, the hybrid layer was found to be thinner in the apical areas by some authors [46,47]. A recent article reported that radicular dentin in the apical third is often sclerotic and the tubules are filled with minerals that resemble those from peritubular dentin. This process starts in the third decade of life and progresses in an apical-coronal direction. It is a potential impediment to effective dentin adhesion and will require further investigation [48].

Problems with Adhesive Materials

Technique Sensitivity

Uniform application of material and evaporation of alcohol or acetone carrier deep in the canal is nearly impossible to achieve due to the complex anatomy of the root canal [49]. Once the primer is applied, the volatile carrier must be evaporated. This can also be problematic in the apical one-third [50]. Bouillguet 2003, reported bonding to flat radicular sample produces higher bond strengths [51]. An excessively thick layer of luting around a fiber post to compensate for the fit of the post is an unfavorable factor for the long-term success of post-retained restorations, owing to the high polymerization shrinkage leading to a high frequency of decementation [12,52]. Also resins in thin layers generate very high forces from polymerization contraction [53-56]. Passive retention of the post is improved if it fits snugly into the prepared space and if the luting layer is fine and even. Post decementation generally occurs at the dentine/cement interface due to the bubbles and pores that form as a result curing shrinkage [12,57-59].

Total Etch Vs Self-Etch Systems

Endodontic instrumentation produces a thick smear layer, total etch removes this thick endodontic smear layer, residual dentin debris and produces higher bond strength than self-etch systems [60-62]. Some studies have demonstrated similarities between bond strengths for self-etch and etch-and-rinse adhesives in different regions of coronal dentin [63-66]. Numerous authors have reported that fiber post cementation with the resin cement associated with etch-and-rinse adhesive may generate greater bonding potential than self-etch adhesive, which may be due to mild etching effect of self-etch [67-70]. But there are problems of technique sensitivity with total-etch systems such as those of over-etching, control of humidity within the canal, incomplete infiltration, bond deterioration and nanoleakage. Hence it was suggested that self-etch systems could be used in a simplified manner [71,72].

Light Curing

Resin adhesive systems can be classified as light cured, self-cured, dual-cured and self-adhesive cements. Irrespective of the type of bonding agent, limited access to curing light within the root canal may hinder the photopolymerization of the adhesives. Light transmitting posts had light transmitting capacity of 0-40%, decreasing from coronal to apical level and also that even without a post, the luminous intensity inside the canal decreased to levels that are insufficient for polymerization, especially in the apical third [73,74]. Based on these findings, the use of light-cured resin cements for post placement cannot be recommended. The benefits of light-transmitting posts are unclear [75,76]. Studies show higher bond strengths and improved hybridization along the root canal for self or dual-polymerized adhesives [77-79].

Self or Dual-Polymerized Adhesives

Self-cured materials, however, offer worse handling characteristics due to their relatively fast, uncontrolled polymerization and lower bond strengths. Because the acid is not rinsed off after application, residual acid can partially neutralize the high pH amines in the self-cured component of the adhesive or sealer, making them less effective in the chemical polymerization process [80-83]. It has been demonstrated, however, that the attenuated light penetration interferes with the cement polymerization toward the apical areas of the root canal and sometimes even when translucent fiber posts are used and the self-cure mechanism for dual-cured materials alone is not only slower but also less effective than the use of light-activation [84-90]. It is also known that self or dual-cured resins cements are not compatible with simplified adhesives (i.e., two-step etch-and-rinse or self-etch agents). This incompatibility is due to the low pH of simplified adhesives, which may react to the basic tertiary amines used as self-cure co-initiators, interfering with proper polymerization. Thus, non-simplified adhesives (three-step etch-and-rinse systems, for instance) should be used for bonding fiber post to root canals using regular resin cements [84].

The second problem with the self-etching adhesive systems when used with self- or dual-cured resins is that they are highly hydrophilic and act as permeable membranes. The chemical polymerization process is slow. Extended setting time for self-cured resins is beneficial for stress relief, but the prolonged time allows diffusion of moisture from the dentin through the hydrophilic primer, which creates water blisters along the interface with the slow polymerizing resins. This moisture contamination reduces bond strength and facilitates leaching of water-soluble components from the resin, which may further contribute to the breakdown of the bond [81,83,91-94].

Self-Adhesive Cements

Studies have reported, however, limited etching potential for self-adhesive cements compared to etch and-rinse and self-etch adhesives when luting fiber based post. Self-adhesive cements may also present lower degrees of C - C conversion and poorer mechanical properties than regular resin cements [95-98]. The lower etching aggressiveness and suboptimal properties may account for the low early (immediate) interfacial strengths reported for fiber post luted with self-adhesive cements [99].

The results of a recent systematic review and meta-analysis of *in vitro* studies suggest that the use of self-adhesive resin cement could improve the retention of glass-fiber posts as compared with regular resin cements, the authors concluded that articles included in this meta-analysis showed high heterogeneity and high risk of bias [100].

Effect of Irrigants and Sealers

NaOCl and chelating agents that contain hydrogen peroxide leave behind an oxygen-rich layer on the dentin surface. Oxygen is one of the many substances that inhibit the polymerization of resins. When dentin bonding agents are applied to an oxygen-rich surface, low bond strengths are achieved and microleakage is increased [101-103]. It has been expressed that residual calcium hydroxide paste could prevent effective bonding in some areas; that it can act as a physical barrier, and that the high pH may act to neutralize the acid primer in self-etching adhesives [104-106].

Retreatment is always a concern with a new material. Resilon is soluble in chloroform and other solvents, and several studies show it is easily removed by a variety of methods. Epiphany, on the other hand, like other resins, is not soluble in the solvents commonly used in dentistry. Removal of resin sealers from fins and accessory canals or deep bifurcated canals is difficult. Removing bonded resin is likely to be that much more difficult [107-109]. Eugenol is one of many substances that inhibits the polymerization reaction of resins and can interfere with bonding [110,111].

Custom Fiber Post

Individual post fitting system is to use a fiberglass mesh, inserting it into the canal to act as the post. This technique showed that the number of gaps observed with a scanning electron microscope was greater with this system than with prefabricated posts [112].

Silanization

Silanization is the technique used most often to enhance the bond strength of fiber-based post to the luting cement achieve this goal. Silane coupling agents are bifunctional molecules, with one end of the molecule capable of reacting with inorganic glass-fiber and the other with an organic resin. The highly crosslinked polymer matrix of a fiber-based post is virtually non-reactive, therefore, only the exposed fibers on the post surface could provide sites for chemical bonding with the silane molecules. The use of silanes to improve the bonding of resin luting agents to fiber-based post is, however, a controversial topic. Randomized controlled trials are needed to confirm whether the use of silane influences the bond strength of fiber-based post [113].

Bond Deterioration

Another limitation of dentin bonding is deterioration of the resin bond with time. This is a process that is well documented *in vitro* and *in vivo* [28-38]. Interfacial leakage increases as the bond degrade [114,115]. In the root canal system where torsional and flexural forces stress the dentin/resin interface repeatedly during function and parafunction, the bond degradation is enhanced. Repeated stress causes microfractures and cracks in the resin. Unpolymerized resin also contributes to the breakdown of the bond [116].

One of the most important factors in the strength and stability of the resin/dentin bond is the completeness of resin infiltration into the demineralized dentin. If the resin doesn't completely infiltrate, fluid movement between the hybrid layer and unaffected dentin speeds the degradation of the bond [117,118]. This process is enhanced by enzymes released by bacteria and from the dentin itself [119]. The breakdown products diffuse out of the interfacial area, which weakens the bond, and allows more fluid to ingress. Collagen degradation is thought to occur via host-derived matrix metalloproteinases (MMPs) that are present in dentin and bacteria and released slowly over time [116]. Prolonged etching times may create a demineralized zone that is too deep for effective resin infiltration, resulting in a weaker bond and accelerated degradation [120,121].

Interesting Fact

Just when these problems were been reported, studies found that the bonding of fiber-based post to the dental structure may be related more to the friction of the post along the canal walls than to the adhesive bonding to root dentin [82]. The use of resin cements, however, has been found to significantly increase the retention of fiber posts and improve the fracture resistance of the bonded structures when compared to other cements [96,122,123].

Another interesting finding is that custom cast posts showed significantly greater bond strength than prefabricated posts when luted with either resin or zinc phosphate cements, which questions the second advantage of fiber-based post [124-126].

Aesthetics vs Survival

It is undeniable fact that fiber-based post provide better aesthetic than cast post. Aesthetics plays important role in the smile zone, i.e the anterior region. However, a long-term study that evaluated 10-year survival of glass fiber supported prosthodontic restorations revealed relatively high annual failure rate of glass reinforced fiber posts. On the other hand, anterior teeth were more prone to failure [127]. In another prospective study for detecting the major risk factors for failure. In terms of tooth location, higher failure rates were detected in anterior teeth compared to the posterior. It was also found that incisors or canines had about 3 times the failure rate of restorations placed in premolars or molars Hence the significance of the third major advantage of the fiber-based post is also lost [5,58].

Other Problems

The radiopacity is very less compared to metal post [128]. A study employing finite element analysis has suggested that fiber-posts produce greater stresses within the root canal when exposed to thermal change than metal post systems. They state that the high thermal conductivity of metal posts leads to a reduced temperature gradient throughout the restored system whereas a reduced heat flow into dentine with non-metal posts may cause a concentration of thermal stresses and this may lead to cement failure and recommend the use of a metal post and core [19].

Survival Rate - Cast Post Vs Fiber Post

The first and foremost problem with studies on fiber based is lack of considerable follow of studies i.e ranging from few months to a year to two. Unlike the studies on cast post which have a follow up ranging from 10-25 years. Glazer (2000) who reported the results of a perspective with 47 patients a follow-up period ranged between 6.7 and 45.4 months [129]. There were no fractures. The overall failure rate was 7.7% and the cumulative survival rate was 89.6% at the end of the follow-up period. (Of which 3.9% failures were due to the occurrence of periapical lesions) However, the authors criticized their findings by indicating that the length of the follow up was relatively short to make a definite generalization. Naumann *et al.* 2005 conducted a prospective study and evaluated glass fiber reinforced composite post restorations [5]. 105 posts received by 83 patients were followed up to a period of 2 years. One and 2-year failure rates of fiber reinforced composite post restorations were 4 and 12%, respectively. Signifying that the failure rate was three times in the second years. Similar results were also obtained by another retrospective study by Ghavamnasiri *et al.* 2009 who evaluated the success rate in endodontic-treated premolars restored with composite resin and fiber reinforced composite posts with ages ranging between 1 and 6 years [130]. Thirty-eight patients with endodontically treated premolar and anterior teeth that were then restored with a coronoradicular quartz fiber post and extensive composite resin restorations were selected for participation in the study. The overall cumulative survival rate (48.8%) was determined, while the survival probabilities after 1, 2, 4, 5, and 6 years of service were 88.37%, 60.95%, 45.71%, 32.65%, and 0%, respectively. The influence of the remaining coronal structure on the survival of root-filled teeth was explained by some authors. Glazer *et al.*, Ellner *et al.*, Naumann *et al.* and Bitter *et al.* have indicated at least 2 mm of the ferrule to fiber post placement [6,43,129,131]. The percentage of failures increased when the remaining dentin wall was less than 2mm. A 10-year retrospective study by Markus 2007, reported an 11% failure over 10 yrs for cast post. Torbjorner *et al.* 1996 reported a 2.1% failure rate per year for 788 teeth with metal posts during a 5-yr period. Another study calculated the median survival rate of teeth with metal posts to be 17.4 yr [132]. Weine *et al.* 1991 reported 9 failures of 138 teeth restored with cast post and cores [133]. The minimum recall time was 10 yr. In a study with a 25-yr follow-up, the longevity of teeth restored after endodontic treatment with a cast post and core and crown was the same as teeth with vital pulps and crowns [134]. Hence these studies clearly validate the success of cast post over a fiber-based post.

Conclusion

The two sides of the current debate pit the possibility of flexure producing micromovement of the core, cement breakdown, leakage, and failure versus the possibility of reduced catastrophic root fracture. In the absence of an adequate ferrule, failure will occur and the debate centers on whether it is better to have re-restorable failures in the short term or unrestorable failures after a long time in function or at high-stress levels. The few clinical trials suggest, at least in the short term, reasonable success for fiber-based post restorations. However that before these posts are adopted fully in the clinical practice, high-quality long-term randomized controlled prospective clinical trials are necessary, investigating the success of fiber-based post restorations and newer materials such as quartz-fiber posts.

References

1. Bru E, Forner L, Llana C, Almenar A (2013) Fiber post behavior prediction factors. A review of the literature. *J Clin Exp Dent* 5: e150-3.
2. Lassilla LV, Tanner J, Le Bell AM, Narva K, Vallitu PK (2004) Flexural properties of fiber reinforced root canal posts. *Dent Mater* 20: 29-36.
3. Fredriksson M, Astbäck J, Pamenius M, Arvidson K (1998) A retrospective study of 236 patients with teeth restored by carbon fiber-reinforced epoxy resin posts. *J Prosthet Dent* 80: 151-7.
4. Schmitter M, Rammelsberg P, Gabbert O, Ohlmann B (2007) Influence of clinical baseline findings on the survival of 2 post systems: a randomized clinical trial. *Int J Prosthodont* 20: 173-8.
5. Naumann M, Blankenstein F, Dietrich T (2005) Survival of glass fiber reinforced composite post restorations after 2 years-an observational clinical study. *J Dent* 33: 305-12.
6. Naumann M, Sterzenbach G, Franke A, Dietrich T (2007) Randomized controlled clinical pilot trial of titanium vs glass fiber prefabricated posts: preliminary results after up to 3 years. *Int J Prosthodont* 20: 499-503.
7. Mannocci F, Sherriff M, Watson TF (2001) Three-point bending test of fiber posts. *J Endod* 27: 758-61.
8. Tay FR, Pashley DH (2007) Monoblocks in root canals: a hypothetical or a tangible goal. *J Endod* 33: 391-8.
9. Li LL, Wang ZY, Bai ZC, Mao Y, Gao B, *et al.* (2006) Three-dimensional finite element analysis of weakened roots restored with different cements in combination with titanium alloy posts. *Chin Med J* 119 :305-11.
10. Cormier CJ, Burns DR, Moon P (2001) In vitro comparison of the fracture resistance and failure mode of fiber, ceramic, and conventional post systems at various stages of restoration. *J Prosthodont* 10: 26-36.

11. Purton DG, Love RM (1996) Rigidity and retention of carbon fiber versus stainless steel root canal posts. *Int Endod J* 29: 262-5.
12. Grande N, Butti A, Plotino G, Somma F (2006) Adapting fiber-reinforced composite root canal post for use in noncircular-shaped canals. *Pract Proced Aesthet Dent* 18: 593-9.
13. Cohen S, Hargreaves KM (2010) *Pathways of the pulp*. Tenth edition.
14. Schwartz R, Robbins J (2004) Post Placement and Restoration of Endodontically Treated Teeth: A Literature Review. *J Endod* 30: 289-301.
15. Purton DG, Payne JA (1996) Comparison of carbon fiber and stainless steel root canal posts. *Quintessence Int* 27: 93-7.
16. Sidoli GE, King PA, Setchell DJ (1997) An in vitro evaluation of a carbon fiber-based post and core system. *J Prosthet Dent* 78: 5-9.
17. Segerström S, Astback J, Ekstrand KD (2006) A retrospective long-term study of teeth restored with prefabricated carbon fiber reinforced epoxy resin posts. *Swed Dent J* 30: 1-8.
18. Drummond JL, Toepke TR, King TJ (1999) Thermal and cyclic loading of endodontic posts. *Eur J Oral Sci* 107: 220-4.
19. Yang HS, Lang LA, Guckes AD, Felton DA (2001) The effect of a thermal change on various dowel-and-core restorative materials. *J Prosthet Dent* 86: 74-80.
20. Miettinen VM, Narva KK, Vallitu PK (1999) Water sorption, solubility, and effect of post-curing glass fiber reinforced polymers. *Biomaterials* 20(13): 1187-94.
21. Torbjørner A, Karlsson S, Syverud M, Hensten-Pettersen A (1996) Carbon fiber reinforced root canal posts. Mechanical and cytotoxic properties. *Eur J Oral Sci* 104: 605-11.
22. Plotino G, Grande M, Pameijer H, Somma F (2008) Influence of surface remodeling using burs on the macro and micro surface morphology of anatomically formed fiber posts. *Int Endod J* 41: 345-55.
23. Al-Omari WM, Zagibeh AM (2010) The retention of cast metal dowels fabricated by direct and indirect techniques. *J Prosthodont* 19: 58-63.
24. Ferrari M, Cagidiaco MC, Goracci C, Vichi A, Mason PN, et al. (2007) Long-term retrospective study of the clinical performance of fiber posts. *Am J Dent* 20: 287-91.
25. Carvalho RM, Pereira JC, Yoshiyama M, Pashley DH (1996) A review of polymerization contraction: the influence of stress development versus stress relief. *Oper Dent* 21: 17-24.
26. Braga RR, Ferracane JL (2004) Alternatives in polymerization contraction stress management. *Crit Rev Oral Biol Med* 15: 176-84.
27. Braga RR, Ferracane JL, Condon JR (2002) Polymerization contraction stress in dual-cure cements and its effect on the interfacial integrity of bonded inlays. *J Dent* 30: 333-40.
28. Inoue S, Vargas MA, Abe Y, Yoshida Y, Lambrechts P, et al. (2001) Microtensile bond strength of eleven contemporary adhesives to dentin. *J Adhes Dent* 3: 237-45.
29. Hashimoto M, Ohno H, Endo K, Kaga M, Sano H, et al. (2000) The effect of hybrid layer thickness on bond strength: demineralized dentin zone of the hybrid layer. *Dent Mater* 16: 406-11.
30. Hashimoto M, Ohno H, Sano H, Kaga M, Oguchi H (2003) Degradation patterns of different adhesives and bonding procedures. *J Biomed Mater Res* 66: 324-30.
31. Hashimoto M, Ohno H, Sano H, Kaga M, Oguchi H (2003) In vitro degradation of resin-dentin bonds analyzed by microtensile bond test, scanning and transmission electron microscopy. *Biomaterials* 24: 3795-803.
32. Hashimoto M, Ohno H, Sano H, Tay FR, Kaga M (2002) Micromorphological changes in resin-dentin bonds after 1 year of water storage. *J Biomed Mater Res* 63: 306-11.
33. Armstrong SR, Vargas MA, Chung I (2004) Resin-dentin interfacial ultrastructure and microtensile dentin bond strength after five-year water storage. *Oper Dent* 29: 705-12.
34. de Oliveira Carrilho MR, Tay FR, Pashley DH, Tjaderhane L, Carvalho RM (2005) Mechanical stability of resin-dentin bond components. *Dent Mater* 21: 232-41.
35. De Munck J, Braem M, Wevers M, Yoshida Y, Inoue S, et al. (2005) Micro-rotary fatigue of tooth-biomaterial interfaces. *Biomaterials* 26: 1145-53.
36. Frankenberger R, Strobel WO, Kramer N, Lohbauer U, Winterscheidt J (2003) Evaluation of the fatigue behavior of the resin-dentin bond with the use of different methods. *J Biomed Mater Res B Appl Biomater* 67: 712-21.
37. Hashimoto M, Ohno H, Kaga M, Endo K, Sano H, et al. (2000) In vivo degradation of resin-dentin bonds in humans over 1 to 3 years. *J Dent Res* 79: 1385-91.
38. Hashimoto M, Ohno H, Kaga M, Endo K, Sano H, et al. (2001) Resin-tooth adhesive interfaces after a long-term function. *Am J Dent* 14: 211-5.
39. Yoshikawa T, Sano H, Burrow MF, Tagami J, Pashley DH (1999) Effects of dentin depth and cavity configuration on bond strength. *J Dent Res* 78: 898-905.
40. Hannig M, Friedrichs C (2001) Comparative in vivo and in vitro investigation of interfacial bond variability. *Oper Dent* 26: 3-11.
41. Roulet JF (1994) Marginal integrity: clinical significance. *J Dent* 22: 9-12.
42. Ferrari M, Mannocci F, Vichi A, Cagidiaco MC, Mjor IA (2000) Bonding to a root canal: structural characteristics of the substrate. *Am J Dent* 13: 255-60.
43. Bitter K, Paris S, Martus P, Schartner R, Kielbassa AM (2004) A Confocal Laser Scanning Microscope investigation of different dental adhesives bonded to root canal dentine. *Int Endod J* 37: 840-8.
44. Mjor IA, Smith MR, Ferrari M, Mannocci F (2001) The structure of dentine in the apical region of human teeth. *Int Endod J* 34: 346-53.
45. Katebzadeh N, Dalton BC, Trope M (1998) Strengthening immature teeth during and after apexification. *J Endodon* 24: 256-9.
46. Yoshiyama M, Carvalho RM, Sano H, Horner JA, Brewer PD, et al. (1996) Regional bond strengths of resins to human root dentine. *J Dent* 24: 435-42.
47. Yoshiyama M, Matsuo T, Ebisu S, Pashley D (1998) Regional bond strengths of self-etching/ self-priming adhesive systems. *J Dent* 26: 609-16.
48. Paque F, Luder HU, Sener B, Zehnder M (2006) Tubular sclerosis rather than the smear layer impedes dye penetration into the dentine of endodontically instrumented root canals. *Int Endod J* 39: 18-25.
49. Tay FR, Pashley DH, Yoshiyama M (2002) Two modes of nanoleakage expression in single-step adhesives. *J Dent Res* 81: 472-6.
50. Schwartz RS (2006) Adhesive Dentistry and Endodontics. Part 2: Bonding in the Root Canal System-The Promise and the Problems: A Review. *J Endod* 32: 1125-34.
51. Bouillaguet S, Troesch S, Wataha JC, Krejci I, Meyer JM, et al. (2003) Microtensile bond strength between adhesive cements and root canal dentin. *Dent Mater* 19: 199-205.

52. Grandini S, Goracci C, Monticelli F, Borracchini A, Ferrari M (2005) SEM evaluation of the cement layer thickness after luting two different posts. *J Adhes Dent* 7: 235-40.
53. Feilzer AJ, de Gee AJ, Davidson CL (1998) Curing contraction of composites and glass ionomer cements. *J Prosthet Dent* 59: 297-300.
54. Feilzer AJ, de Gee AJ, Davidson CL (1987) Setting stress in composite resin in relation to the configuration of the restoratives. *J Dent Res* 66: 1636-9.
55. Feilzer AJ, de Gee AJ, Davidson CL (1989) Increased wall-to-wall curing contraction in thin bonded resin layers. *J Dent Res* 68: 48-50.
56. Alster D, Feilzer AJ, de Gee AJ, Davidson CL (1997) Polymerization contraction stress in thin resin composite layers as a function of layer thickness. *Dent Mater* 13: 146-50.
57. Perez BE, Barbosa SH, Melo RM, Zamboni SC, Ozcan M, et al. (2006) Does the thickness of the resin cement affect the bond strength of a fiber post to the root dentin? *Int J Prosthodont*. 19: 606-9.
58. Naumann M, Reich S, Nothdurft F, Dietrich T (2008) Survival of glass fiber post restorations over 5 years. *Am J Dent* 21: 267-72.
59. D'Arcangelo C, Cinelli M, De Angelis F, D'Amario M (2007) The effect of resin cement film thickness on the pull-out strength of a fiber-reinforced post system. *J Prosthet Dent* 98: 193-8.
60. Goracci C, Sadek FT, Fabianelli A, Tay FR, Ferrari M (2005) Evaluation of the adhesion of fiber posts to intraradicular dentin. *Oper Dent* 30: 627-35.
61. Leirskar J, Nordbo H (2000) The effect of zinc oxide-eugenol on the shear bond strength of a commonly used bonding system. *Endod Dent Traumatol* 16: 265-8.
62. Zhang L, Huang L, Xiong Y, Fang M, Chen JH, et al. (2008) Effect of post-space treatment on retention of fiber posts in different root regions using two self-etching systems. *Eur J Oral Sci* 116: 280-6.
63. Akagawa H, Nikaido T, Takada T, Burrow ME, Tagami J (2002) Shear bond strengths to coronal and pulp chamber floor dentin. *Am J Dent* 15: 383-8.
64. Kijssamanmith K, Timpawat S, Harnirattisai C, Messer HH (2002) Micro-tensile bond strengths of bonding agents to pulpal floor dentine. *Int Endod J* 35: 833-9.
65. Tanumiharja M, Burrow ME, Tyas MJ (2000) Microtensile bond strengths of seven dentin adhesive systems. *Dent Mater* 16: 180-7.
66. Toledano M, Osorio R, Ceballos L, Fuentes MV, Fernandes CA, et al. (2003) Microtensile bond strength of several adhesive systems to different dentin depths. *Am J Dent* 16: 292-8.
67. Hayashi M, Okamura K, Wu H, Takahashi Y, Koytchev EV, et al. (2008) The root canal bonding of chemical-cured total-etch resin cements. *J Endod* 34: 583-6.
68. Mazzoni A, Marchesi G, Cadenaro M, Mazzotti G, Di Lenarda R, et al. (2009) Push-out stress for fiber posts luted using different adhesive strategies. *Eur J Oral Sci* 117: 447-53.
69. Radovic I, Mazzitelli C, Chieffi N, Ferrari M (2008) Evaluation of the adhesion of fiber posts cemented using different adhesive approaches. *Eur J Oral Sci* 116: 557-63.
70. Valandro LF, Filho OD, Valera MC, de Araujo MA (2005) The effect of adhesive systems on the pullout strength of a fiberglass-reinforced composite post system in bovine teeth. *J Adhes Dent* 7: 331-6.
71. Hashimoto M, Ohno H, Kaga M, Sano H, Tay FR, et al. (2002) Over-etching effects on micro-tensile bond strength and failure patterns for two dentin bonding systems. *J Dent* 30: 99-105.
72. Akagawa H, Nikaido T, Takada T, Burrow ME, Tagami J (2002) Shear bond strengths to coronal and pulp chamber floor dentin. *Am J Dent* 15: 383-8.
73. Teixeira EC, Teixeira FB, Piasick JR, Thompson JY (2006) An in vitro assessment of prefabricated fiber post systems. *J Am Dent Assoc* 137: 1006-12.
74. Faria e Silva AL, Arias VG, Soares LE (2007) Influence of fiber-post translucency on the degree of conversion of a dual-cured resin cement. *J Endod* 33: 303-5.
75. Boff LL, Grossi ML, Prates LH, Burnett LH, Shinkai RS (2007) Effect of the activation mode of post adhesive cementation on push-out bond strength to root canal dentin. *Quintessence Int* 38: 387-94.
76. Abou-Id LR, Morgan LE, Silva GA, Poletto LT, Lanza LD, et al. (2012) Ultrastructural evaluation of the hybrid layer after cementation of fiber posts using adhesive systems with different curing modes. *Braz Dent J* 23: 116-21.
77. Akgungor G, Akkayan B (2006) Influence of dentin bonding agents and polymerization modes on the bond strength between translucent fiber posts and three dentin regions within a post space. *J Prosthet Dent* 95: 368-78.
78. Vichi A, Carrabba M, Goracci C, Ferrari M (2012) Extent of cement polymerization along dowel space as a function of the interaction between adhesive and cement in fiber post cementation. *J Adhes Dent* 14: 51-7.
79. Faria e Silva AL, Casselli DS, Ambrosano GM, Martins LR (2007) Effect of the adhesive application mode and fiber post translucency on the push-out bond strength to dentin. *J Endod* 33: 1078-81.
80. Sanares AM, Ithagarun A, King NM, Tay FR, Pashley DH (2001) Adverse surface interactions between one-bottle light-cured adhesives and chemical-cured composites. *Dent Mater* 17: 542-56.
81. Tay FR, Pashley DH, Yiu CK, Sanares AM, Wei SH (2003) Factors contributing to the incompatibility between simplified-step adhesives and chemically-cured or dual-cure composites: part I. Single-step self-etching adhesive. *J Adhes Dent* 5: 27-40.
82. Goracci C, Sadek FT, Fabianelli A, Tay FR, Ferrari M (2005) Evaluation of the adhesion of fiber posts to intraradicular dentin. *Oper Dent* 30: 627-35.
83. Tay FR, Suh BI, Pashley DH, Prati C, Chuang SF, et al. (2003) Factors contributing to the incompatibility between simplified-step adhesives and self-cured or dual-cured composites: part II. Single-bottle, total-etch adhesive. *J Adhes Dent* 5: 91-105.
84. Baena E, Fuentes M, Garrido M, Rodriguez J, Ceballos L (2012) Influence of post-cure time on the microhardness of self-adhesive resin cements inside the root canal. *Oper Dent* 37: 548-56.
85. Cerutti F, Acquaviva PA, Gagliani M, Ferrari M, Mangani F, et al. (2011) Degree of conversion of dual-cure resins light-cured through glass-fiber posts. *Am J Dent* 24: 8-12.
86. Shadman N, Atai M, Ghavam M, Kermanshah H, Ebrahimi SF (2012) Parameters affecting the degree of conversion of dual-cure resin cements in the root canal: FTIR analysis. *J Can Dent Assoc* 78: c53.
87. Roberts HW, Leonard DL, Vandewalle KS, Cohen ME, Charlton DG (2004) The effect of a translucent post on resin composite depth of cure. *Dent Mater* 20: 617-22.
88. Faria-e-Silva AL, Moraes RR, Ogliaeri FA, Piva E, Martins LR (2009) Panavia F: the role of the primer. *J Oral Sci* 51: 255-9.
89. Moraes RR, Faria-e-Silva AL, Ogliaeri FA, Correr-Sobrinho L, Demarco FF, et al. (2009) Impact of immediate and delayed light activation on self-polymerization of dual-cured dental resin luting agents. *Acta Biomater* 5: 2095-100.

90. Reges RV, Moraes RR, Correr AB, Sinhoreti MA, Correr-Sobrinho L, et al. (2008) In-depth polymerization of dual-cured resin cement assessed by hardness. *J Biomater Appl* 23: 85-96.
91. Tay FR, Pashley DH (2003) Have dentin adhesives become too hydrophilic? *J Can Dent Assoc* 69: 726-31.
92. Tay FR, Frankenberger R, Krejci I (2004) Single-bottle adhesives behave as permeable membranes after polymerization. I. In vivo evidence. *J Dent* 32: 611-21.
93. Chersoni S, Suppa P, Grandini S (2004) In vivo and in vitro permeability of one-step self-etch adhesives. *J Dent Res* 83: 459-64.
94. Chersoni S, Acquaviva GL, Prati C, Ferrari M, Grandini S, et al. (2005) In vivo fluid movement through dentin adhesives in endodontically treated teeth. *J Dent Res* 84: 223-7.
95. Calixto LR, Bandeca MC, Clavijo V, Andrade MF, Vaz LG, et al. (2012) Effect of resin cement system and root region on the push-out bond strength of a translucent fiber post. *Oper Dent* 37: 80-6.
96. Gomes GM, Gomes OM, Reis A, Gomes JC, Loguercio AD, et al. (2011) Regional bond strengths to root canal dentin of fiber posts luted with three cementation systems. *Braz Dent J* 22: 460-7.
97. Goracci C, Tavares AU, Fabianelli A, Monticelli F, Raffaelli O, et al. (2004) The adhesion between fiber posts and root canal walls: comparison between microtensile and push-out bond strength measurements. *Eur J Oral Sci* 112: 353-61.
98. Moraes RR, Boscatto N, Jardim PS, Schneider LF (2011) Dual and self-curing potential of self-adhesive resin cements as thin films. *Oper Dent* 36: 635-42.
99. Sadek FT, Goracci C, Monticelli F, Grandini S, Cury AH, et al. (2006) Immediate and 24-hour evaluation of the interfacial strengths of fiber posts. *J Endod* 32: 1174-7.
100. Sarkis-Onofre R, Skupien JÁ, Cenci MS, de Moraes RR, Pereira-Cenci T (2014) The role of resin cement on bond strength of glass-fiber posts (GFPs) luted into root canals: a systematic review and meta-analysis of in vitro studies. *Oper Dent* 39: E31-44.
101. Lai SC, Mak YF, Cheung GS, Osorio R, Toledano M (2001) Reversal of compromised bonding to oxidized etched dentin. *J Dent Res* 80: 1919-24.
102. Ari H, Yasar E, Belli S (2003) Effects of NaOCl on bond strengths of resin cements to root canal dentin. *J Endod* 29: 248-51.
103. Erdemir A, Ari H, Gungunes H, Belli S (2004) Effect of medications for root canal treatment on bonding to root canal dentin. *J Endod* 30: 113-6.
104. Sevimay S, Oztan MD, Dalat D (2004) Effects of calcium hydroxide paste medication on coronal leakage. *J Oral Rehabil* 31: 240-4.
105. Lambrianidis T, Margelos J, Beltes P (1999) Removal efficiency of calcium hydroxide dressing from the root canal. *J Endod* 25: 85-8.
106. Kim SK, Kim YO (2002) Influence of calcium hydroxide intracanal medication on the apical seal. *Int Endod J* 35: 623-8.
107. Ezzie E, Fleury A, Solomon E, Spears R, He J (2006) Efficacy of retreatment techniques for a resin-based root canal obturation material. *J Endod* 32: 341-4.
108. de Oliveira DP, Barbizam JV, Trope M, Teixeira FB (2006) Comparison between gutta-percha and Resilon removal using two different techniques in endodontic retreatment. *J Endod* 32: 362-4.
109. Schirmermeister JF, Meyer KM, Hermanns P, Altenburger MJ, Wrbas KT (2006) The effectiveness of hand and rotary instrumentation for removing a new synthetic polymer-based root canal obturation material (Epiphany) during retreatment. *Int Endod J* 39: 150-6.
110. Macchi RL, Capurro MA, Herrera CL, Cebada FR, Kohen S (1992) Influence of endodontic materials on the bonding of composite resin to dentin. *Endod Dent Traumatol* 8: 26-9.
111. Ngho EC, Pashley DH, Loushine RJ, Weller RN, Kimbrough WF (2001) Effects of eugenol on resin bond strengths to root canal dentin. *J Endod* 27: 411-4.
112. Santos V, Perdigão J, Gomes G, Silva AL (2009) Sealing ability of three fiber dowel systems. *J Prosthodont* 18: 566-76.
113. de Moraes AD, Cenci MS, de Moraes RR, Pereira-Cenci T (2013) Current concepts on the use and adhesive bonding of glass-fiber posts in dentistry: a review. *Applied Adhesion Science* 1: 4.
114. Okuda M, Pereira PN, Nakajima M, Tagami J, et al. (2002) Long-term durability of the resin-dentin interface: nanoleakage vs. microtensile bond strength. *Oper Dent* 27: 289-96.
115. Okuda M, Pereira PN, Nakajima M, Tagami J (2001) Relationship between nanoleakage and long-term durability of dentin bonds. *Oper Dent* 26: 482-90.
116. De Munck J, Van Landuyt K, Peumans M (2005) A critical review of the durability of adhesion to tooth tissue: methods and results. *J Dent Res* 84: 118-32.
117. Pashley DH, Tay FR, Yiu C (2004) Collagen degradation by host-derived enzymes during aging. *J Dent Res* 83: 216-21.
118. Paul SJ, Welter DA, Ghazi M, Pashley D (1999) Nanoleakage at the dentin-adhesive interface vs microtensile bond strength. *Oper Dent* 24: 181-8.
119. Santerre JP, Shajii L, Leung BW (2001) Relation of dental composite formulations to their degradation and the release of hydrolyzed polymeric-resin-derived products. *Crit Rev Oral Biol Med* 12: 136-51.
120. Pioch T, Stotz S, Buff E, Duschner H, Staehle HJ (1998) Influence of different etching times on hybrid layer formation and tensile bond strength. *Am J Dent* 11: 202-6.
121. Van Landuyt KL, Kanumilli P, De Munck J, Peumans M, Lambrechts P, et al. (2006) Bond strength of a mild self-etch adhesive with and without prior acid-etching. *J Dent* 34: 77-85.
122. Mendoza DB (1997) Root reinforcement with a resin bonded preformed post. *J Prosthet Dent* 78: 10-4.
123. Cohen BI, Pagnillo MK, Newman I, Musikant BL, Deutsch AS (2000) Retention of four endodontic posts cemented with composite resins. *Gen Dent* 48: 320-4.
124. O'Keefe KL, Miller BH, Powers JM (2000) In vitro tensile bond strength of adhesive cements to new post materials. *Int J Prosthodont* 13: 47-51.
125. Drummond JL (2000) In vitro evaluation of endodontic posts. *Am J Dent* 13: 5B-8B.
126. Gallo JR, Miller T, Xu X, Burgess JO (2002) In vitro evaluation of the retention of composite fiber and stainless steel posts. *J Prosthodont* 11: 25-9.
127. Sterzenbach G, Franke A, Naumann M (2012) Rigid versus flexible dentine-like endodontic posts—Clinical testing of a biomechanical concept, Seven-year results of a randomized controlled clinical pilot trial on endodontically treated abutment teeth with severe hard tissue loss. *J Endod* 38: 1557-63.
128. Schwartz RS, Robbins JW (2004) Post placement and restoration of endodontically treated teeth: A literature review. *J Endod* 30: 289-301.
129. Glazer B (2000) Restoration of endodontically treated teeth with carbon fiber posts—a prospective study. *J Can Dent Assoc* 66: 613-8.
130. Ghavamnasiri M, Maleknejad F, Ameri H, Moghaddas MJ, Farzaneh F, et al. (2011) A retrospective clinical evaluation of success rate in endodontic-treated premolars restored with composite resin and fiber reinforced composite posts. *Journal of Conservative Dentistry* 14: 378-82.

131. Ellner S, Bergendal T, Bergman B (2003) Four post-and-core combinations as abutments for fixed single crowns: a prospective up to 10-year study. *Int J Prosthodont* 16: 249-54.
132. Nanayakkara L, McDonald A, Setchell DJ (1999) Retrospective analysis of factors affecting the longevity of post crowns. *J Dent Re* 78: 222.
133. Weine FS, Wax AH, Wenckus CS (1991) Retrospective study of tapered, smooth post systems in place for 10 years or more. *J Endodon* 17: 293-7.
134. Valderhaug J, Jokstad A, Ambjornsen E, Norheim PW (1997) Assessment of the periapical and clinical status of crowned teeth over 25 years. *J Dent* 25: 97-105.

Submit your next manuscript to Annex Publishers and benefit from:

- ▶ Easy online submission process
- ▶ Rapid peer review process
- ▶ Online article availability soon after acceptance for Publication
- ▶ Open access: articles available free online
- ▶ More accessibility of the articles to the readers/researchers within the field
- ▶ Better discount on subsequent article submission

Submit your manuscript at

<http://www.annexpublishers.com/paper-submission.php>